

PRODUCTION OF FLUORINE-BASED POROUS HOLLOW YARN MEMBRANE**Publication number:** JP4187224**Publication date:** 1992-07-03**Inventor:** KAMINE YASUHIRO; KIKUYA NOBUYUKI; HIRAI
TAKAYUKI; KAMO JUN**Applicant:** MITSUBISHI RAYON CO**Classification:****- international:** **B01D71/32; B01D71/00;** (IPC1-7): B01D71/32**- European:****Application number:** JP19900312768 19901120**Priority number(s):** JP19900312768 19901120**Report a data error here****Abstract of JP4187224**

PURPOSE: To obtain a porous hollow yarn high in mechanical strength and having a thick film by melt-spinning an ethylene-chlorotrifluoroethylene copolymer and stretching the obtained yarn to make it porous. **CONSTITUTION:** An ethylene-chlorotrifluoroethylene copolymer is melt-spun with a hollow yarn producing nozzle to obtain an unstretched crystalline hollow yarn which is highly oriented. The spinning temp. has to be controlled to 240-280 deg.C, and the yarn fiber is wound at 100-4000 yarn forming draft. Since the crystallinity of the unstretched hollow yarn obtained is not sufficiently yet, it is heat-treated (annealed) at 180-240 deg.C preferably in an inert gas atmosphere. The crystal structure is then not relaxed but broken and cold-stretching at <70 deg.C by 10-100%. The cold-stretched yarn hot-stretching at 70-160 deg.C. The total stretching rate is controlled in this case to 30-400% after hot stretching.

Data supplied from the **esp@cenet** database - Worldwide